



(11) Publication number : **0 590 983 A1**

(12)

## EUROPEAN PATENT APPLICATION

(21) Application number : 93307778.6

(51) Int. Cl.<sup>5</sup> : **C04B 24/16, C04B 24/26,  
C08F 220/06**

(22) Date of filing : 30.09.93

(30) Priority : 30.09.92 JP 286763/92  
30.08.93 JP 238741/93

(43) Date of publication of application :  
06.04.94 Bulletin 94/14

(84) Designated Contracting States :  
DE FR GB

(71) Applicant : Takemoto Yushi Kabushiki Kaisha  
2-5, Minato-machi  
Gamagouri-shi Aichi-ken (JP)

(72) Inventor : Kinoshita, Mitsuo  
308, Shiinoki, Tametou-cho  
Toyokawa-shi, Aichi-ken (JP)  
Inventor : Miura, Yoshimasa  
55 Nakayashiki, Ugalke-cho  
Nishio-shi, Aichi-ken (JP)  
Inventor : Arashima, Takeshi  
1-2 Shimogotanda, Hirata-cho  
Gamagouri-shi, Aichi-ken (JP)

(74) Representative : Ablewhite, Alan James  
MARKS & CLERK 57/60 Lincoln's Inn Fields  
London WC2A 3LS (GB)

(54) **Cement dispersion agents.**

(57) Cement dispersion agents composed of water-soluble vinyl copolymers obtained by aqueous solution radical polymerization of four or five specified kinds of monomers at a ratio within a specified range can provide improved fluidity to high-strength hardened concrete and mortar with extremely low water-to-cement ratio.

EP 0 590 983 A1

Background of the Invention

This invention relates to cement dispersion agents. More particularly, this invention relates to cement dispersion agents capable of providing high fluidity to high-strength cement compounds with extremely low water-to-cement ratio and reducing the drop in the fluidity with the passage of time after mixing.

It has been known to use condensation products of naphthalene sulfonic acid and formaldehyde, condensation products of melamine sulfonic acid and formaldehyde or water-soluble vinyl copolymers as a cement dispersion agent. If such a prior art cement dispersion agent is used to produce a high-strength cement compound and, in particular, if it is desired to produce an ultra high-strength cement compound with extremely low water-to-cement ratio of less than 20% in order to obtain hardened concrete and mortar with compressive strength greater than 1100kgf/cm<sup>2</sup>, however, neither condensation products of naphthalene sulfonic acid and formaldehyde nor condensation products of melamine sulfonic acid and formaldehyde is capable of providing any fluidity to such a cement compound. If use is made of water-soluble vinyl copolymers (such as disclosed in U.S. Patent 4,962,173 and Japanese Patent Application Tokkai 3-93660), it is not possible to provide sufficient fluidity to such cement compounds and the drop in whatever fluidity that has been provided with the passage of time after mixing (referred to as the slump loss) is large. It now goes without saying that workability becomes extremely poor if sufficient fluidity cannot be provided to a cement compound and the slump loss is large.

Summary of the Invention

The problem to be solved by the present invention is that prior art cement dispersion agents, when used to produce high-strength cement compounds, cannot provide high fluidity to the produced high-strength cement compounds and that the slump loss is large.

The present inventors discovered, as a result of their diligent research in order to find solutions to this problem, that use as cement dispersion agent should be made of a water-soluble vinyl copolymer obtained by aqueous solution radical copolymerization of four or five specified kinds of monomers at specified ratios of copolymerization.


Detailed Description of the Invention

This invention relates to cement dispersion agents comprising water-soluble vinyl copolymers obtained by aqueous solution radical copolymerization of a first monomer shown by Formula (1) given below, a second monomer shown by Formula (2) given below, a third monomer shown by Formula (3) given below, a fourth monomer shown by Formula (4) given below and optionally a fifth monomer shown by Formula (5) given below such that the ratio of constituent monomer units is (First monomer)/(Second monomer)/(Third monomer)/(Fourth monomer)/(Fifth monomer) = 45-65/8-23/3-25/5-25/0-15 (molar %) as converted to monomers, where:


Formula (1) is




Formula (2) is




Formula (3) is




Formula (4) is



Formula (5) is



where  $\text{R}^1$ ,  $\text{R}^2$ ,  $\text{R}^3$ ,  $\text{R}^4$  and  $\text{R}^6$  are each H or  $\text{CH}_3$ ;  $\text{R}^5$  and  $\text{R}^7$  are each an alkyl group with 1-3 carbon atoms; X is  $-\text{SO}_3\text{M}^1$  or an organic group shown by Formula (6) given below;  $\text{M}^1$  is an alkali metal, an alkali earth metal, ammonium or organic amine; m is an integer 1-30; n is an integer 5-25; Formula (6) is



and  $\text{M}^2$  is an alkali metal, an alkali earth metal, ammonium or organic amine.

Examples of the first monomer shown by Formula (1) include salts of alkali metals, salts of alkali earth metals and alkanol amine salts of (meth)acrylic acid. Examples of the second monomer shown by Formula (2) include (i) methallylsulfonates such as alkali metal salts, alkali earth metal salts and alkanol amine salts of methallylsulfonic acid; and (ii) p-methallyloxybenzene sulfonates such as alkali metal salt, alkali earth metal salts and alkanol amine salts of p-methallyloxybenzene sulfonic acid. Examples of the third monomer shown by Formula (3) include polyethyleneglycol mono(meth)allylether and methoxy polyethyleneglycol (meth)allylether each with molar number of additive ethylene oxide within the range of 1-30 and preferably 5-25. Examples of the fourth monomer shown by Formula (4) include alkoxy polyethyleneglycol (meth)acrylates such as (meth)acrylates of methoxy polyethyleneglycol, ethoxy polyethyleneglycol, propoxy polyethyleneglycol and isopropoxy polyethyleneglycol each with the molar number of additive ethylene oxide within the range of 5-25. Examples of the fifth monomer shown by Formula (5) include alkyl(meth)acrylates such as methyl(meth)acrylate, ethyl(meth)acrylate, propyl(meth)acrylate and isopropyl(meth)acrylate.

As explained above, the water-soluble vinyl copolymers of the present invention are obtained by aqueous solution radical copolymerization of first, second, third, fourth and fifth monomers respectively shown by Formulas (1), (2), (3), (4) and optionally (5), but their copolymerization ratio (as converted to these monomers) is in the range of (First monomer)/(Second monomer)/(Third monomer)/(Fourth monomer)/(Fifth monomer) = 45-65/8-23/3-25/5-25/0-15(molar %) and more preferably in the range of 50-62/10-20/5-20/7-20/1-12(molar %). If a fifth monomer shown by Formula (5) is optionally copolymerized, its ratio is generally 0.1-15 molar %, and it is preferably 1-12 molar %. If the ratio of any of these monomers falls out of the given range, the water-soluble vinyl copolymer which is obtained cannot exhibit the desired effects as a cement dispersion agent. Among the water-soluble vinyl copolymers thus obtained, those with average numerical molecular weight within the range of 2000-20000 (Pullulan converted by GPC method) are desirable from the point of view of fluidity provided to cement compounds when this is used as a cement dispersion agent and the effect on prevention of slump loss.

Of the five kinds of monomers shown by Formulas (1)-(5), the second and third monomers shown by Formulas (2) and (3) are particularly important. If methallylsulfonate and p-methallyloxybenzene sulfonate are used simultaneously as a second monomer shown by Formula (2), in particular, the water-soluble vinyl monomer thereby obtained can provide even more improved fluidity to cement compositions mixed with microscopic powder admixtures such as silica fume, blast-furnace slag and fly ash as binder. The third monomer shown by Formula (3) serves to provide high fluidity even to ultra high-strength cement compounds with extremely low water-to-cement ratio of less than 25%.

The water-soluble vinyl copolymers of the present invention are obtained by aqueous solution radical co-

polymerization of the monomers described above at specified copolymerization ratios in the presence of a radical initiator. As for the method of copolymerization, it is important to use water or a mixture of water and a water-soluble organic solvent in an aqueous solution polymerization process. This may be done, for example, by first dissolving each monomer in water and preparing an aqueous solution containing each monomer with total content of 10-45%. Next, this aqueous solution is kept in a nitrogen gas, and a radical initiator is added for a radical copolymerization reaction at 50-70°C for 5-8 hours to obtain a water-soluble vinyl copolymer. There is no limitation as to the kind of radical initiator to be used for this purpose as long as it is dissociated at the temperature of copolymerization reaction to initiate radical polymerization, but it is preferable that the radical initiator is water-soluble. Examples of such water-soluble radical initiator include potassium persulfate, ammonium persulfate, hydrogen peroxide and 2,2'-azobis(2-amidinopropane) dihydrochloride. They can also be used as a redox initiator by combining with a reducing agent such as sulfites and L-ascorbic acid or an amine.

Cement dispersion agents of the present invention comprise water-soluble vinyl copolymers as explained above, but other agents can also be used together, depending on the purpose of the use. Examples of such other agents include air-entraining agents, antifoaming agents, coagulation accelerators and retarders, anti-rust agents, antiseptics and water-proofing agents. If they are to be used, they may be kneaded when the cement compound is prepared and added with water, or they may be added to the cement compound after it is kneaded.

Cement dispersion agents of this invention can be used when mortar and concrete are produced by using a binder composed of cement or a mixture of cement and a microscopic powder admixture. Examples of cement to be used include many kinds of portland cement such as ordinary portland cement, high early strength portland cement and moderate heat portland cement, fly ash cement, blast furnace cement, silica cement and many kinds of blended cement. Examples of microscopic powder admixture include silica fume, blast-furnace slag and fly ash. They are used usually at the rate of 0.1-2.0 weight % as converted to solid component with respect to the binder comprised of cement or a mixture of cement and a microscopic powder admixture. If too little is used, fluidity cannot be provided to the cement compound to a desirable degree, and the effect of preventing slump loss is adversely affected. The process of kneading itself may become difficult and hardened mortar and concrete of only poor quality may be obtained. If too much is used, on the other hand, setting retardation becomes too great, affecting the hardening process adversely. In some cases, segregation may result and it becomes difficult to obtain uniformly hardened mortar and concrete.

Cement dispersion agents of the present invention are capable, in particular, of providing high fluidity to cement compounds with extremely low water-to-cement ratio with content of binder 600-800kg/m<sup>3</sup> or more preferably 700-800kg/m<sup>3</sup>, and water-to-binder (weight) ratio of greater than 15% and less than 25%, or more preferably greater than 15% and less than 20%, and high-strength hardened mortar and concrete can be obtained by using a cement dispersion agent of the present invention.

Next, examples will be presented in order to describe the invention more clearly but these examples are not intended to limit the scope of the invention. In what follows, "parts" will mean "weight parts" and "%" will mean "weight %" except where the amount of air is considered.

## Examples

### Part 1 (Synthesis of Water-Soluble Vinyl Copolymers As Cement Dispersion Agents)

#### Test Example 1

Methacrylic acid 54 parts (0.628 moles), sodium methallylsulfonate 18 parts (0.114 moles), sodium p-methallyloxybenzene sulfonate 10 parts (0.04 moles), polyethyleneglycol (with n = 8, where n signifies throughout herein the molar number of added ethylene oxide) monoallylether 40 parts (0.098 moles), methoxypolyethyleneglycol (n=23) methacrylate 128 parts (0.120 moles), methyl acrylate 11 parts (0.128 moles) and ion exchange water 260 parts were placed inside a flask and dissolved with stirring. Next, a 30% aqueous solution of sodium hydroxide 84 parts was added to neutralize the methacrylic acid until the pH value of the reacting system was adjusted to 8.5. Next, the temperature of the reacting system was kept at 60°C by means of a warm bath, and after the interior of the reacting system was replaced by nitrogen gas, a 20% aqueous solution of ammonium persulfate 30 parts was added as polymerization initiator to start polymerization. After four hours of reaction, a 20% aqueous solution of ammonium persulfate 15 parts was further added and the reaction was continued for three more hours to complete the polymerization. A 30% aqueous solution of sodium hydroxide was added for neutralizing acid decomposition products and a reaction product was obtained by completely neutralizing the reaction system. In order to remove monomers which have not reacted, the product was condensed by means of an evaporator, and after it was precipitated in petroleum ether and filtered, it was vacuum-

dried to obtain refined water-soluble vinyl copolymer (A-1) 275 parts.

Water-soluble vinyl copolymer (A-1) was analyzed by UV absorption, NMR, atomic light absorption, elemental analysis, GPC and titration methods. It was learned that its carboxyl value was 128. Its sulfur content was 1.74% and its Na<sub>2</sub>O content was 8.8% by elemental analyses. The content of sodium p-methallyloxybenzene sulfonate was 3.5% by UV absorption. It was learned from the NMR analysis that its copolymerization ratio (as converted to each monomer) was (sodium methacrylate)/(sodium methallylsulfonate) / (sodium p-methallyloxybenzene sulfonate)/(polyethyleneglycol (n=8) monoallylether)/(methoxypolyethyleneglycol (n=23) methacrylate)/(methyl acrylate) = 56/10/3.5/9/10.5/11 (molar ratio) and the average numerical molecular weight was 3600 (hereinafter Pullulan converted by GPC method).

#### Test Examples 2-6 and Comparison Examples 1-7)

As in Test Example 1, water-soluble vinyl copolymers (A-2)-(A-6) listed in Table 1 and water-soluble vinyl copolymers (R-1)-(R-7) listed in Table 2 were obtained.

Table 1

Kind	Kinds of monomer and their copolymerization ratio (molar %)										Average Molecular Weight
	Monomer-a		Monomer-b		Monomer-c		Monomer-d		Monomer-e		
	a-1	a-2	b-1	b-2	c-1	c-2	d-1	d-2	e-1		
A-1		56	10	3.5	9		10.5		11		3600
A-2		60	8	5	15		10		2		5600
A-3		55	13		12		12		8		2900
A-4		51	11			15		20	3		8400
A-5	61		9	3		10	11		6		12000
A-6		60	15		15		10				5200

Table 2

Kind	Kinds of monomer and their copolymerization ratio (molar %)										Average Molecular Weight
	Monomer-a		Monomer-b		Monomer-c		Monomer-d		Monomer-e		
	a-1	a-2	b-1	b-2	c-1	c-2	d-1	d-2	e-1		
R-1		70					30				8000
R-2		60	10				20		10		3500
R-3		60			20		10		10		10000
R-4	50		2			33	15				4500
R-5	35			20	10			15	20		25000
R-6		63	8				29				5800
R-7	70		12					18			7500

In Tables 1 and 2:

Monomers-a, -b, -c, -d and -e: Monomers shown by Formulas (1), (2), (3), (4) and (5), respectively;

a-1: Sodium acrylate;

a-2: Sodium methacrylate;

b-1: Sodium methallylsulfonate;

b-2: Sodium p-methallyloxybenzene sulfonate;

c-1: Polyethyleneglycol (n=8) monoallyl ether;

c-2: Polyethyleneglycol (n=4) monoallyl ether;

d-1: Methoxypolyethyleneglycol (n=23) methacrylate;

d-2: Methoxypolyethyleneglycol (n=9) methacrylate;

e-1: Methyl acrylate.

## Part 2 (Preparation and Evaluation of Concrete)

### Preparation of Concrete

Ordinary portland cement, silica fume, fine aggregates and coarse aggregates were sequentially placed inside a pan-type mixer with capacity of 50 liters under the two different conditions (1) and (2) shown in Table 3 such that the target slump would be 25cm and the target amount of air would be less than 2%. Water-soluble vinyl copolymers synthesized in Part 1 and serving as cement dispersion agent and an antifoaming agent (polyoxyethylene (6 moles)/polyoxypropylene (40 moles) block oleylether) were kneaded together and added with water for a mixing process at 20° for 3 minutes to obtain concrete. The kinds and added amounts of these water-soluble vinyl copolymers used as cement dispersion agents are shown in Tables 4 and 5.

### Method of Evaluation

For each concrete thus prepared, the slump, the amount of air and the compressive strength at 7 days and 28 days were measured according respectively to JIS(Japanese Industrial Standards)-A1101, JIS-A1128 and JIS-A1108. The slump was measured both immediately after the kneading and after 60 minutes. The results are shown in Tables 4 and 5.

Table 3

Condi- tion	Water-to- binder ratio (%)	Ratio of silica fume in binder (%)	Target slump (cm)	Sand-coarse aggregate ratio (%)	Used materials (kg/m <sup>3</sup> )			
					Binder Cement	Silica fume	Water	Fine Aggregates
1	20	0	25	35.3	750	0	150	1018
2	19	10	25	35.6	663	74	140	1018

In Table 3:

Binder: Cement + silica fume;

Cement: Ordinary portland cement (specific weight = 3.16);

Silica fume: Micro Silica 940U produced by Elkem, Inc. (specific weight = 2.20);

Fine aggregates: Sand from Oigawa River (specific weight = 2.63, finesse modulus = 2.71);

Coarse aggregates: Gravel from Danto (specific weight = 2.61, finesse module = 6.65).

Table 4

Test No.	Condi- tion	Cement dispersion agent Kind Amount	Slump (cm)		Amount of air (%)	Compressive strength (kgf/cm <sup>2</sup> )	
			Immediately after	After 60 min.		at 7 days	at 28 days
1	(1)	A-1 1.0	25.8	24.2	1.1	970	1230
2	(1)	A-2 1.3	25.4	24.1	1.3	940	1180
3	(1)	A-3 1.4	25.6	23.4	1.2	930	1160
4	(1)	A-4 1.5	25.3	23.6	1.3	950	1190
5	(1)	A-5 1.4	25.7	23.8	1.0	960	1240
6	(1)	A-6 1.3	25.3	24.0	1.3	950	1190
7	(2)	A-1 0.8	25.4	24.2	1.0	970	1320
8	(2)	A-3 1.3	25.2	23.2	1.1	990	1330



Table 5

Test No.	Condi- tion	Cement dispersion agent Kind	Amount	Slump (cm)		Amount of air (%)	Compressive strength (kgf/cm <sup>2</sup> )	
				Immediately after	After 60 min.		at 7 days	at 28 days
9	(1)	R-1	2.5	*3	--	--	--	--
10	(1)	R-2	2.5	25.8	16.2	1.7	840	1010
11	(1)	R-3	2.5	*3	--	--	--	--
12	(1)	R-4	2.5	*3	--	--	--	--
13	(1)	R-5	2.5	*3	--	--	--	--
14	(1)	*2	2.2	*3	--	--	--	--
15	(2)	R-1	2.5	*3	--	--	--	--
16	(1)	R-6	2.0	25.3	13.5	1.8	850	990
17	(1)	R-7	2.0	25.2	13.0	2.0	840	980
18	(2)	R-6	1.5	*3	--	--	--	--
19	(2)	R-7	1.5	*3	--	--	--	--

In Tables 4 and 5:

Amount of cement dispersion agent: Ratio of solid component (%) with respect to the binder;

Amount of antifoaming agent: Added by 0.005 weight % with respect to binder for all test examples except none

was added to No. 6;

\*2: Condensation product of naphthalene sulfonic acid and formaldehyde;





\*3: Did not become a slurry and could not be kneaded for mixing.

In summary, cement dispersion agents of the present invention make it possible to provide high fluidity to high-strength cement compounds and, in particular, to ultra high-strength cement compounds, reducing their slump loss, and to obtain high-quality ultra high-strength hardened concrete and mortar with improved workability.


## Claims

1. A cement dispersion agent comprising water-soluble vinyl copolymer obtained by aqueous solution radical copolymerization of a first monomer given by Formula (1), a second monomer given by Formula (2), a third monomer given by Formula (3), a fourth monomer given by Formula (4) and optionally a fifth monomer given by Formula (5) at copolymerization ratio of 45-65/8-23/3-25/5-25/0-15 in molar % as converted to monomers;


Formulas (1), (2), (3), (4) and (5) being given respectively by



and



where  $\text{R}^1$ ,  $\text{R}^2$ ,  $\text{R}^3$ ,  $\text{R}^4$  and  $\text{R}^6$  are each H or  $\text{CH}_3$ ;  $\text{R}^5$  and  $\text{R}^7$  are each an alkyl group with 1-3 carbon atoms; X is  $-\text{SO}_3\text{M}^2$  or an organic group shown by



$\text{M}^1$  is an alkali metal, an alkali earth metal, ammonium or organic amine; m is an integer 1-30; n is an integer 5-25; and  $\text{M}^2$  is an alkali metal, an alkali earth metal, ammonium or organic amine.

2. The cement dispersion agent of claim 1 wherein the average numerical molecular weight of said water-soluble vinyl copolymer is 2000-20000.
3. The cement dispersion agent of claim 1 or claim 2 which is usable for producing concrete of which the unit content of binder composed of cement or a mixture of cement and microscopic powder admixture is 600-800kg/m<sup>3</sup> and the water-to-binder ratio is over 15% and less than 25%.

4. The cement dispersion agent of claim 1 or claim 2 which is usable for producing concrete of which the unit content of binder composed of cement or a mixture of cement and microscopic powder admixture is 700-800kg/m<sup>3</sup> and the water-to-binder ratio is over 15% and less than 20%.
5. The cement dispersion agent of any of claims 1 to 4, in which the first monomer shown by Formula (1) is selected from salts of alkali metals, alkaline earth metals or alkanolamines with (meth)acrylic acid.
6. The cement dispersion agent of any of claims 1 to 5 in which the third monomer shown by Formula (3) comprises polyethyleneglycol mono(meth)allylether or methoxy polyethyleneglycol (meth)allylether each with a molar number of additive ethylene oxide of from 1-30.
7. The cement dispersion agent of any of claims 1 to 6 in which the fourth monomer shown by Formula (4) is selected from alkoxy polyethyleneglycol (meth)acrylates with a molar number of additive ethylene oxide of from 5-25.
8. The cement dispersion agent of any of claims 1 to 7 in which the fifth monomer shown by Figure (5) is selected from alkyl(meth)acrylates.
9. The cement dispersion agent of any of claims 1 to 8, in which the copolymerization ratio is 50-62/10-20/5-70/7-20/1-12 (molar %).
10. The cement dispersion agent of any of claims 1 to 9, in which the second monomer comprises methallyl-sulfonate and p-methallyloxybenzene sulfonate.



European Patent  
Office

## EUROPEAN SEARCH REPORT

Application Number  
EP 93 30 7778

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.5)
X	EP-A-0 448 717 (NIPPON SHOKUBAI KAGAKU KOGYO CO. LTD.) * abstract; claims 1,2,9 * * page 4, line 32 - page 6, line 28 * * page 7, line 50 - page 8, line 8 * * page 10, line 56 - page 12, line 20; example 126 *	1,2,5-7, 10	C04B24/16 C04B24/26 C08F220/06
Y	---	8	
P,Y	EP-A-0 549 280 (TAKEMOTO YUSHI KABUSHIKI KAISHA) * abstract; claims 1,2,4 * * page 3, line 3 - line 38 * * page 7, line 1 - line 54 *	8	
A	---	1,2,5,7, 8,10	
D,A	EP-A-0 331 308 (TAKEMOTO YUSHI KABUSHIKI KAISHA) * abstract; claims 1-5,10,11,15 * * page 4, line 46 - page 5, line 41; example 1 *	1,2,5,7, 10	TECHNICAL FIELDS SEARCHED (Int.Cl.5)
A	EP-A-0 291 590 (NIPPON SHOKUBAI KAGAKU KOGYO CO., LTD.) * abstract; claims 1,5,9 * * page 2, line 41 - page 3, line 47; example 1 *	1,2,5,7	C04B C08F
A	EP-A-0 271 784 (NATIONAL STARCH AND CHEMICAL COORPORATION) * abstract; claim 1 * * page 2, line 35 - line 51 * * page 10, line 37 - page 12, line 1 * -----	1,10	
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 7 January 1994	Examiner Olsson-Norgren, S
<p><b>CATEGORY OF CITED DOCUMENTS</b></p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons ----- A : member of the same patent family, corresponding document</p>			

EPO FORM 150 (01.92) (P0402)